

PRODUCT DATA SHEET



PDS No: 1022

Product Details

Product Code: EZIT230, EZIT235, EZIT233, EZIT234
Product Name: Ezicover Aquanamel SemiGloss
Other Name(s): Ezicover Aquanamel SemiGloss White, Ezicover Aquanamel SemiGloss Midtone, Ezicover Aquanamel SemiGloss UltraDeep, Ezicover Aquanamel SemiGloss, ExtraBright

Description

Ezicover Aquanamel SemiGloss is a new generation premium grade semi gloss paint based on 100% acrylic emulsion. It is water based and hence environmentally friendly. It has very good resistance to water, scratches and general weather conditions. It is very easy to apply, gives excellent flow-out and is free from solvents.

Uses- Ideal for kitchen, bathrooms and laundries

Features and Benefits

- Excellent flow and application levelling properties
- Convenient water wash-up with the hardness of an enamel finish
- Also suitable for properly prepared timber, doors, wallboard, plywood, window frames and furniture
- Suitable for interior & exterior use
- Contains dry film mould inhibitors

Limitations and Precautions

- **Do Not** apply when the surface temperature is below 10°C or above 35°C
- Check the weather forecast. **Do Not** apply if rain, heavy dew or a sudden drop in temperature is likely during application or during the first 12 hours after application
- **Do Not** apply if humidity is 85% or above
- **Allow a week's curing in normal conditions to achieve the desired properties**
- Being thermoplastic, the film is sensitive towards alcohol and aromatic hydrocarbons
- Avoid cleaning the paint surface in the first 4 – 6 weeks
- Always test cleaning solutions to make sure they will not damage the paint surface
- Some insect treatments contain chemicals that can soften and stain painted surfaces.

PRODUCT DATA SHEET



PDS No: 1022

Physical Properties

Resin Type	Acrylic Emulsion
Pigmentation	Titanium Dioxide and Inert Extenders
Colour	White and APCO Colour World colours
Gloss at 60° head	25-30
Specific Gravity(Kg/Ltr)	1.05-1.35
Coverage (m²/Ltr)	10-14
No. of coats	Two
Dry Times(at 20°C and 60%RH)*	30 min
*(cooler temperatures, higher film thickness and higher humidity can extend the drying and subsequently the recoat time)	
Recoat time	2 hrs
Flash Point	Not applicable
Packaging Sizes	10L,4L,1L
Thinner and cleanup	Water (May be thinned upto 5% depending on weather conditions when applying by spray)
Theoretical VOC(g/Ltr)	41-47

Surface Preparation

Remove all dust, dirt, grease, loose and flaking paint suitably by thorough cleaning. If some mould or fungus is present, then treat with **APCO Biowash (SDS 4009)** as a moss and mould remover

Previously painted surfaces should be sanded using 180-220 grit sandpaper (depending on surface condition) to remove loose or flaking paint and to reduce the previous film to a flat finish.

Clean with a wet sponge and allow the surface to dry

Undercoat Requirements

Use one coat of **Ezicover Alkyd Primer Undercoat (SDS 4029)** or **Ezicover Acrylic Sealer Undercoat (SDS 1003)**

Sand the surface lightly using 220 grit sandpaper and dust off the area to be painted. The surface is now ready for application.

Application and Process

Stir the contents thoroughly before and during use

Apply two liberal coats of **Ezicover AquanameL SemiGloss**

Apply liberal coats by brush roller or airless spray

PRODUCT DATA SHEET

PDS No: 1022

For Best Results

- The use of an 8 – 10mm nap roller is recommended
- Allow a minimum of 2 hours prior to sanding and recoating
- When repainting check **cross cut adhesion** of the old paint on the surface

Health and Safety

- Please refer to Safety Data Sheet (**SDS 1021**) before use
- Use in well ventilated areas
- **First Aid:**
 - Eyes and Skin irritation – Wash with large amounts of fresh running water
 - If swallowed – drink 2-3 glasses of water and seek appropriate medical advice

Storage

Store in cool, well ventilated areas away from direct sunlight. Keep containers tightly sealed.

Spillage and Disposal

Use rags or sawdust to contain any spill and then dispose of through a commercial waste disposal organisation.

*Please refer to the updated versions of Safety data sheet(SDS) and Technical Data sheet (TDS) before using any **APCO** Product.*

KEEP OUT OF REACH OF CHILDREN

APCO Coatings (NZ) Limited

Ph. (09) 2733 041. Fax. (09) 2733 045. Physical Add. 14 Ron Driver Place, East Tamaki, Auckland 2013

The information and recommendations set down here in this document are presented in good faith and believed to be correct, APCO Coatings (NZ) Ltd gives no guarantee to the completeness and accuracy thereof.

APCO Coatings (NZ) Ltd is not be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the Technical Data Sheet refers.