

## **ezi•cover**

### **Acrylic DTS**

**Direct To Substrate**

#### **Description:**

Ezicover Acrylic DTS is an adhesion promoted, 100% acrylic that has been developed specifically to achieve excellent long-term exterior protection and durability. Can be applied to most surfaces without the use of a primer. Having excellent tannin block properties, it is ideal for use on new timber.

#### **Features and Benefits:**

- 
- 
- Excellent flow on application which gives a smooth finish
- Self-Priming. Excellent adhesion to correctly prepared new and existing surfaces without the need of a primer.
- Suitable for coastal areas.
- Tough, flexible resin for long-term protection.
- Available in Low Sheen, Semi Gloss & Gloss.

#### **Limitations:**

- Do not apply when ambient temperature is below 10°C or surface temperature is above 40°C.
- Do not apply to timber surfaces that are showing signs of deterioration.

#### **Technical Data:**

<b>Resin Type:</b>	100% Acrylic Emulsion
<b>Pigmentation:</b>	Titanium dioxide and inert extenders
<b>Solvents:</b>	Water
<b>Colour:</b>	Super White and a range of tint bases
<b>Gloss Level:</b>	Low Sheen Semi Gloss 23% Gloss 75-85%
<b>Dry-Time:</b>	30 mins Touch, 2 hour overcoat
<b>Coverage:</b>	12 - 14 m <sup>2</sup> per litre
<b>No. of coats:</b>	Two or Three
<b>Packaging sizes:</b>	4 and 10 litre
<b>Flash Point:</b>	None
<b>Thinner:</b>	Water
<b>VOC:</b>	Low Sheen 51 g/l Semi Gloss 51 g/l Gloss 44 g/l



### **Surface Preparation:**

The surface must be thoroughly cleaned to remove all traces of dust, dirt, moss, oil and grease, bird droppings etc. All areas of degraded paint must be sanded smooth, all nail holes and other defects primed and filled with suitable filler. New galvanising must be degreased with detergent prior to painting. Use an anticorrosive Zinc Phosphate primer on ferrous metal. Moss and mould can be removed with APCO Biowash.

### **Application:**

Apply two or three liberal coats, at the recommended coverage rate, to a properly prepared surface. Allow at least 2 hours drying between coats. To keep brushes and rollers working freely, rinse occasionally with clean water.

### **For Best Results:**

- 1) Applying the product liberally by brush will ensure maximum contact with the surface.
- 2) If applying by roller: on a smooth surface, a sleeve of 8 – 10mm nap is recommended, for semi rough surfaces, use rollers of 12 – 15mm nap. Please use the most suitable application for the job.
- 3) With repaints, spot prime with Ezicover Acrylic DTS followed by two full coats of the same topcoat.
- 4) On new work and in coastal areas, apply three full coats to ensure maximum surface protection.

**Health and Safety:** (Please refer to Material Safety Data Sheet before using)

**Ezicover Acrylic DTS** is essentially non-flammable and non-hazardous.

### **KEEP OUT OF REACH OF CHILDREN**



0800 BUY APCO  
Ph. 09) 2733 041  
Fax. 09) 2733 045

PO Box 58849  
Botany  
Manukau 2163

**V1.2**  
**17/04/14**

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, APCO Coatings (NZ) Ltd makes no representation as to the completeness and accuracy thereof. In no event will APCO Coatings (NZ) Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers