



ezi•cover

Aquanamel

Product Description:

An ultra premium, new generation 100% Acrylic emulsion based paint. It is water based and hence environmentally friendly. It has very good resistance to water, scratches and general weather. It is very easy to apply and gives excellent flow-out. Low odour and free from solvents. Available in Low Sheen, Semi Gloss & Gloss finishes.

Features and Benefits:

- Contains dry film mould inhibitors
- Excellent flow and application properties
- Convenient water wash-up with the hardness of an enamel finish
- Suitable for interior & exterior use.

Areas of Application:

Timber, doors, wallboard, plywood, window frames, furniture, kitchens, bathrooms and laundries.

Technical Data:

Resin Type	Acrylic Emulsion
Pigmentation	Titanium dioxide and inert extenders
Colour	Super White & a range of tint bases
Gloss Levels	Low Sheen: 8 – 10% Semi Gloss: 30 - 40% Gloss: 70 - 75%
Solvent Resistance	Being thermoplastic, the film is sensitive to alcohol & aromatic hydrocarbons
Coverage	10 - 14 sq. m. /ltr per coat. Practical coverage may depend on surface profile, method of application and loses. Two coats of finishing are recommended
Dry Times (at 25° C & RH 60%)	Touch Dry : 30 minutes Hard Dry : 16 hrs Recoat Time : 4 hrs
Packaging Sizes	1, 4 and 10 litre
Thinner	Water. Use up to 10% for thinning if required depending on climatic conditions.
VOCs	Low Sheen: 54 Semi Gloss: 54 Gloss: 57

Method of Application:

Brush, Roller or Spray. Please use the method best suited to your requirement and skill.

Surface Preparation:

Remove all dust, dirt, grease, loose and flaking paint suitably by thorough cleaning. If mould or fungus is present, treat with APCO Biowash.

Clean with water and allow the surface to dry. Use the appropriate Sealer or Primer eg Ezicover Alkyd Primer Undercoat, Ezicover Acrylic Primer Undercoat or Ezicover Acrylic Sealer Undercoat. On tannin rich timber, use one coat of Ezicover All 'n One Primer. Sand the surface lightly and dust off the area to be painted. The surface is now ready for finishing.

Application:

Stir the contents thoroughly before and during use. Apply two coats of Aquanamel. Apply liberal coats by brush, roller or airless spray.

For Best Results:

- 1) Do not apply when the surface temperature is below 10° C.
- 2) In normal conditions, a week's curing is required to develop full hardness and resistance properties.
- 3) Use good quality brushes & rollers.

Health and Safety: (Please refer to Material Safety Data Sheet before using)

Ezicover Aquanamel is non-flammable and essentially non-hazardous

KEEP OUT OF REACH OF CHILDREN



0800 BUY APCO
Ph. 09) 2733 041
Fax. 09) 2733 045

PO Box 58849
Botany
Manukau 2163

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, APCO Coatings NZ Ltd makes no representation as to the completeness and accuracy thereof. In no event will APCO Coatings NZ Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers