

**Technical Data Sheet:**  
**Product No: EZBHB101**



## **ezi•cover**

# **Smooth-Coat**

### **Description:**

Ezi-Cover Smooth-Coat is specifically formulated as a surface equalizer/primer/sealer for interior broad wall, paper-faced plasterboard walls and ceilings. Its unique formulation smooth's out minor surface irregularities and textural differences. Correctly applied over paper-faced plasterboard, Smooth-Coat imparts a surface suitable for a **Level 5 paint finish** requiring minimal sanding. Smooth-Coat may also be used over timber and properly prepared, previously painted surfaces.

It has been specifically formulated for air-less spray application, but can also be applied by brush or roller.

### **Features and Benefits:**

- Excellent adhesion to stopped paper faced plasterboard, air-dry and gypsum based stopping and finishing compounds.
- Free sanding and even porosity imparting smooth finishes.
- Very little dust when sanding.
- Minimum grain and surface raising.
- Self-Priming.

### **Limitations:**

- Not recommended for wet areas.
- Not suitable for very old, porous surfaces.
- Do not apply when ambient temperature is below 10°C or surface temperature is above 40°C.

### **Technical Data:**

<b>Resin Type:</b>	100% Acrylic Emulsion
<b>Pigmentation:</b>	Inorganic pigments and extenders
<b>Solvents:</b>	Water
<b>Colour:</b>	White
<b>Gloss Level:</b>	Matt
<b>Density:</b>	1.48 Kgs/ Litre
<b>Dry-Time:</b>	10 mins Touch, 2 hour sand and overcoat Cooler temperatures, higher film thickness or high humidity will require longer drying times.
<b>Coverage:</b>	4 m <sup>2</sup> per litre (DFT = 200µ)
<b>No. of coats:</b>	One or Two
<b>Flash Point:</b>	None
<b>Cleaner:</b>	Water
<b>VOC:</b>	< 28 g/l

**Surface Preparation:**

Remove all unsound paint, surface grease and oil, dirt etc. Sand smooth all areas of stopping and fill all holes and other defects with appropriate synthetic filler. On warm days dampen the surface of paper-faced plaster with a wet sponge prior to painting.

**Application:**

Apply one to two liberal coats, by roller or airless spray at the recommended coverage, to the properly prepared surface. Allow at least 2 hours drying time between coats. To keep brushes and rollers working freely, rinse occasionally with clean water. (Cross hatching Air less Spray work)

**For Best Results:**

- 1) Best applied by spray application.
- 2) If applying by roller, than apply liberally with a 10 – 12mm nap roller.
- 3) If applying by brush, than apply liberally, keeping the brush fully loaded.
- 4) On warm dry days, dampen the surface of the board with a wet sponge prior to application.
- 5) Allow at least 2 hours prior to sanding smooth with 200 grit sandpaper or finer.
- 6) Apply 2 coats of Ezicover Smooth-coat, or one coat of Ezicover Smooth-Coat and a second coat of Ezicover Acrylic Sealer Undercoat

**Health and Safety:** (Please refer to Material Safety Data Sheet before using)

**Ezicover Smooth-Coat** is essentially non-flammable and non-hazardous.

**KEEP OUT OF REACH OF CHILDREN**

0800 BUY APCO  
Ph. 09) 2733 041  
Fax. 09) 2733 045

PO Box 58849  
Botany  
Manukau 2163

**V1.4**  
**17/04/14**

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, APCO Coatings NZ Ltd makes no representation as to the completeness and accuracy thereof. In no event will APCO Coatings NZ Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers