



# RAPIDPAVE

## Polyurethane Paving Enamel

**Description**

A premium quality, single pack polyurethane-based paint with good wear resistant properties. It is a tough coating with fast drying characteristics. The product can be recoated in 2 hours.

**Areas of Application**

Suitable for protection of driveways, path and workshop floors made with timber & concrete.

*For exterior and interior use.*

**Technical Data**

Colour range	:	Please refer to the High Performance Colour Chart
Gloss Level	:	20 - 25%
Solvent Resistance	:	Resistance to aliphatic hydrocarbon is good. Polar solvents & chlorinated solvents are liable to attack the film.
Toxicity	:	Dry film is non toxic
Heat Resistance	:	Up to 120 <sup>0</sup> C max.
Thinning & Clean Up	:	Enamel Thinner 600 or Mineral Turpentine. Though this product is designed for undiluted application, it may be thinned up to 10% if necessary.
Coverage	:	16 sq. m. / litre per coat. Practical coverage may depend on surface profile, method of application and losses.
Drying Time (at 25 <sup>0</sup> C & RH 60%)	:	Touch dry : 20 minutes. Recoat : 2 hours Cooler temperatures, higher film thickness or higher humidity conditions will require longer drying time.
Packs available	:	4L, 1L

## Technical Data Sheet:



### Method of Application

Brush, Roller or Spray. Please use the method best suited to your requirement & skill.

### Surface Preparation

*Previously Unpainted Timber Floors* - Sand the surface smooth wipe the surface clean. Apply two coats of RAPIDPAVE Polyurethane Paving Enamel. 10% Thinning is recommended for the first coat.

*Previously Unpainted Concrete Floors* - Smooth bare concrete must be acid etched with diluted hydrochloric acid. Flush the surface with sufficient fresh water. Allow complete drying for 3-4 days. Apply two coats of RAPIDPAVE Polyurethane Paving Enamel, thinning the first coat by 10% with Thinner 600 or Mineral Turps.

*Previously painted surface* Thoroughly remove all loose & flaking paint. Oil, grease & other contaminants should be removed by cleaning with mild detergent solutions. After sanding, touch up select bare areas with RAPIDPAVE Polyurethane Paving Enamel thinned 10%. Follow with two full coats.

### Application

Stir the contents thoroughly before & during use. Apply uniformly direct from the container. When applying over an unknown coating, please test the adhesion & compatibility of this product over a small test area.

### Flammability & Transport Information

Highly flammable, Dangerous goods class 3.2, Flash point 24<sup>0</sup>C UN 1263, PG III

### Safety & Precautions

Do not apply when surface temperature is below 10<sup>0</sup>C

Provide adequate ventilation during use.


Keep out of reach of children

Check cross cut adhesion of old paint before repainting.

In normal condition a week's curing is required to develop full hardness & resistance properties.

### DISCLAIMER:

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.



0800 BUY APCO  
Ph. 09) 2733 041  
Fax. 09) 2733 045

PO Box 58849  
Botany  
Manukau 2163