

APCO Coatings (NZ) Limited

14 Ron Driver Place
East Tamaki
PO Box 58849 Botany
Manukau 2163
0800 BUY APCO



POOLKOTE

Chlorinated Rubber Pool Paint

Description

This product is a premium quality swimming pool paint based on pure chlorinated rubber. It is quick drying and easy to apply. It provides a hardwearing and durable finish, which can be easily cleaned. The product has excellent resistance to acids, chlorine, oxidising and bleaching agents.

Areas of Application

Though mainly designed for concrete swimming pools, the product can also be used for the protection of concrete and primed steel in heavy traffic areas.

Limitations

- Not suitable for fibre-glass (unless sealed with epoxy first)
- Not suitable for heated pools, salt water pools or spa pools

Technical Data

Colour range	:	Ocean Blue, Paradise Blue & Deep Azure
Gloss Level at 600 head	:	20 – 35%
Solvent Resistance	:	Being thermoplastic, film sensitive towards alcohol & aromatic hydrocarbons.
Toxicity	:	Dry film is non-toxic & lead free.
Solvent for Thinning & Clean Up	:	Thinner 601. Use up to 20% thinner depending on weather conditions.
Theoretical Coverage	:	8 to 14m ² /lit per coat. Practical coverage may depend on surface profile, method of application & losses.
Drying Time (at 250C & RH 60%)	:	Touch dry : About 30 minutes. Recoat : 16 hours. Cooler Temperatures, higher film thickness or higher humidity conditions will require longer drying time.
Packs available	:	10L, 4L & 1L
Flash Point	:	32°
VOC	:	455 g/l

Method of Application

Brush Roller or Spray. Please use the method best suited to your requirement and skill.

APCO Coatings (NZ) Limited

14 Ron Driver Place
East Tamaki
PO Box 58849 Botany
Manukau 2163
0800 BUY APCO



Surface Preparation

The surface must be clean and sound. Contaminants like body grease, suntan lotion, oil etc should be completely removed by cleaning. Allow complete drying. The surface should be rough enough to enable good adhesion. (approx. 60 grit).

New concrete surfaces must be fully cured and treated before application of this product.

If painting over old and fully cured chlorinated rubber, this product can be applied directly after proper cleaning.

Application

Stir the content thoroughly using a broad paddle. On a bare concrete and cement render, apply first coat with 20-30% dilution to seal the surface. Follow with 1-2 full coats.

Ensure minimum 16 hours recoating interval.

Do not paint when the temperature is more than 30 degree centigrade and also in windy condition.

In case of repainting, apply one or two full coats depending on the condition of old paint.

Flammability & Transport Information

Highly flammable, Dangerous goods clause 3.2 Flash point less than 25 degree centigrade UN1263 PG III

Safety & Precautions

Do not apply when surface temperature is below 10°C

Allow the paint to dry fully. Forced ventilation is necessary in cold conditions.

The surface should be free from dew and dampness before and during drying.

Always use the recommended thinner for dilution and cleaning.

Please ask for and obtain instruction sheet from Apco Coatings before painting.

KEEP OUT OF REACH OF CHILDREN



0800 BUY APCO
Ph. 09) 2733 041
Fax. 09) 2733 045

PO Box 58849
Botany
Manukau 2163

DISCLAIMER:

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.