

APCO Coatings (NZ) Limited

14 Ron Driver Place
East Tamaki
PO Box 58849 Botany
Manukau 2163
0800 BUY APCO



Technical Data Sheet

Product No: MPTAWT/10L

MPT earthtone 2mm Texture Spray On/Trowel On

Description:

MPT Earthtone 2mm Texture Spray On/Trowel On is formulated on an adhesion promoted pure acrylic latex that imparts excellent adhesion, water and alkali resistance and exceptional weather resistance. It is designed for fast economical spray or trowel on application to interior and exterior masonry surfaces. The high build properties of this coating enhances application on difficult to apply substrates and produces a very tough coating. A dry film thickness of 650 microns per coat can be achieved.

Features and Benefits:

- Forms part of a 10 year warranty paint system
- Excellent adhesion to primed surfaces.
- Also suitable for pre-cast panels that have been sealed with MPT Earthtone Limebuster
- High water and alkali resistance.
- Long term durability
- Available in a range of pastel colours.

Limitations:

Do not apply when ambient temperature is below 10°C or surface temperature is above 45°C. Must be top coated with MPT Earthtone Elastomeric or MPT Earthtone High Build Finish.

Technical Data:

Resin Type:	Adhesion Promoted Pure Acrylic polymer
Pigmentation:	Titanium dioxide and inert extenders
Solvents:	Water
Colour:	White. Can be tinted
Gloss Level:	Low sheen
Density:	1.84 Kgs/ Litre
Dry-Time:	4 hours Touch, 12 hours between recoat in dry conditions
Coverage:	1.5 m ² per litre
No. of coats:	Two
Packaging sizes:	10 litre
Flash Point:	None
Thinner:	Water

APCO Coatings (NZ) Limited

14 Ron Driver Place
East Tamaki
PO Box 58849 Botany
Manukau 2163
0800 BUY APCO



Surface Preparation:

Remove all unsound paint, surface grease, oil, dirt etc. Treat mould affected areas with Biowash.

Application:

Apply as supplied – do not thin.

Apply 2 coats of MPT 2mm Texture Spray On/Trowel On to dry film thickness of 650 microns per coat. Use MPT Elastomeric or MPT High Build Finish as a finish coat. For colours not tinted from White, 2 coats of finish coat are recommended. To assist with drying in cold conditions, add up to 50 grams of white cement per 10L pail.

For Best Results:

- 1) Apply by spray or trowel with a circular motion to achieve an even finish.
- 2) Ensure correct dry film thickness is achieved.
- 3) Allow at least 12 hours before over-coating in summer
- 4) Allow at least 24 hours before over-coating in winter
- 5) Do not apply in direct sunshine.

Health and Safety: (Please refer to Material Safety Data Sheet before using)

MPT 2mm Texture Spray On/Trowel On is essentially non-flammable and non-hazardous.

KEEP OUT OF REACH OF CHILDREN



0800 BUY APCO
Ph. 09) 2733 041
Fax. 09) 2733 045

PO Box 58849
Botany
Manukau 2163