

## APCO Coatings (NZ) Limited

14 Ron Driver Place  
East Tamaki  
PO Box 58849 Botany  
Manukau 2163  
0800 BUY APCO

**APCO** 

paints for the specialist

**Technical Data Sheet:**  
**Product No: EZBHB101**

# APCO EZI-COVER Smooth-Coat

### Description:

Ezicover Smooth-Coat is specifically formulated as a surface equalizer/primer for interior broad wall paper-faced plasterboard walls and ceilings. Its unique formulation smoothes out minor surface irregularities and textural differences. Correctly applied over paper-faced plasterboard, Smooth-Coat imparts a surface suitable for a **Level 5 paint finish** requiring minimal sanding, saving time on plastering.

Smooth-Prep may also be used over timber and properly prepared, previously painted surfaces. It has been specifically formulated for air-less spray application, but also gives excellent results when applied by roller.

### Features and Benefits:

- Excellent adhesion to stopped paper faced plasterboard, air-dry and gypsum based stopping and finishing compounds.
- Free sanding and even porosity imparting smooth finishes.
- Very little dust when sanding.
- Minimum grain and surface raising.
- Self Priming.

### Limitations:

Not recommended for wet areas.

Not suitable for very old, porous surfaces.

**Do not** apply when ambient temperature is below 10°C.

### Technical Data:

<b>Resin Type:</b>	100% Acrylic Emulsion
<b>Pigmentation:</b>	Inorganic pigments and extenders
<b>Solvents:</b>	Water
<b>Colour:</b>	White
<b>Gloss Level:</b>	Matt
<b>Density:</b>	1.48 Kgs/ Litre
<b>Dry-Time:</b>	10 mins Touch, 2 hour sand and overcoat.
<b>Coverage:</b>	Surfacer: 1 coat at 3 – 4 m/L (DFT = 200µ)
<b>No. of coats:</b>	One
<b>Flash Point:</b>	None
<b>Cleaner:</b>	Water

## APCO Coatings (NZ) Limited

14 Ron Driver Place  
East Tamaki  
PO Box 58849 Botany  
Manukau 2163  
0800 BUY APCO



### Surface Preparation:

Remove all unsound paint, surface grease and oil, dirt etc. Sand smooth all areas of stopping and fill all holes and other defects with appropriate synthetic filler. On warm days dampen surface of paper-faced plaster with a wet sponge prior to painting.

### Application:

Apply 1 to 2 liberal coats, by roller or airless spray at the recommended coverage, to the properly prepared surface. Allow at least 2 hours drying time between coats. To keep brushes and rollers working freely rinse occasionally with clean water. (Cross hatching Air less Spray work)

### For Best Results:

- 1) On warm dry days, dampen the surface of the board with a wet sponge prior to application.
- 2) Allow at least 2 hours prior to sanding smooth with 200 grit sandpaper or finer
- 3) Can be over-coated with most acrylic systems.
- 4) For best results over-coat with APCO Pigmented Sealer before top coats.

Health and Safety: (Please refer to Material Safety Data Sheet before using)

**Ezicover Smooth-Coat** is essentially non-flammable and non-hazardous.

**KEEP OUT OF REACH OF CHILDREN**



0800 BUY APCO  
Ph. 09) 2733 041  
Fax. 09) 2733 045

PO Box 58849  
Botany  
Manukau 2163

Version 24.4.13