



TOUCHWOOD Polyurethane Clear

Product Description

This is a premium quality single pack polyurethane clear finish, which enhances the beauty of wood. It is fast drying and offers excellent hardwearing finish. It is available in gloss, semi gloss sheen levels.

Areas of Application

Dressed timber furniture, doors, veneers, wall-paneling etc.

For interior use.

Technical Data

Finish Available	: Gloss & Semi Gloss
Gloss Level at 60° head	: Gloss - Minimum 85 % Semigloss - 20 - 50 % Matt - 0 - 5 %
Solvent Resistance	: Resistance to aliphatic hydrocarbons is good. Polar solvents and chlorinated solvents are liable to attack the film.
Toxicity	: Dry film is non toxic and lead free.
Thinning & Clean Up	: Enamel Thinner 600 / Mineral turps Though the product is designed for undiluted application by brush, up to 5% thinner may be used. When spraying up to 10% thinner may be required depending on weather conditions.
Coverage	:16 sq. m. / litre per coat. Practical coverage may depend on surface profile, method of application and losses.
Drying Time (At 25° C & RH 60%)	:Touch dry : 2 hours Recoat : 16 hours Cooler temperature, higher film thickness or higher humidity conditions will require longer drying times.
Packs available	: 4 L, 1 L, 250ml.



Method of Application

Brush, Roller or Spray. Please use the method best suited to your requirement and skill. The quality of finish may depend on type of wood and its absorption characteristics apart from method of application.

Surface Preparation

Remove all wax, grease and other contaminants by cleaning with mineral turps. Sand the surface uniformly along the grain marks and dust off. Fill the surface imperfections like nail holes, cracks etc by suitable filler. Sand smooth the surface and dust off.

Application

Stir the contents thoroughly before and during use.

On new surfaces, apply one or two coats of Touchwood Polyurethane Clear after 10%, to seal the surface. For very soft and porous timbers, two sealer coats may be required. For hard timbers the sealer coat may require 15% thinning to affect better penetration. Sand the surface lightly after 24 hours to obtain smooth finish. Apply two further coats of Polyurethane clear in desired finish with minimum 16 hours recoating interval. On previously varnished surface, apply one or two coats of Touchwood clear after suitable surface preparation. Transparent stains as desirable can be used prior to application of sealer coat.

Ensure thorough mixing of Semigloss and Matt finishes before application.

Flammability & Transport Information

Highly flammable, Dangerous goods clause 3.2 Flash Point 32° C UN 1263 PG III. Keep away from sources of ignition.

Safety & Precautions

Do not apply when surface temperature is below 10° C

Provide adequate ventilation during use.

Keep out of reach of children.

In normal conditions, a week's curing is required to develop full hardness & resistance properties.

DISCLAIMER:

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products herein described, nor do we accept any liability for loss or damages directly caused by our products. The user is held to check the quality, safety and all other properties of our product prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.



0800 BUY APCO
Ph. 09) 2733 041
Fax. 09) 2733 045

PO Box 58849
Botany
Manukau 2163